# **Structural Analysis Equations**

Lawrence A. Soltis

# **Contents**

Deformation Equations 8–1

Axial Load 8-1

Bending 8-1

Combined Bending and Axial Load 8-3

Torsion 8-4

Stress Equations 8-4

Axial Load 8-4

Bending 8-4

Combined Bending and Axial Load 8–7

Torsion 8-8

Stability Equations 8–8

Axial Compression 8–8

Bending 8-9

Interaction of Buckling Modes 8–10

References 8-11

quations for deformation and stress, which are the basis for tension members and beam and column design, are discussed in this chapter. The first two sections cover tapered members, straight members, and special considerations such as notches, slits, and size effect. A third section presents stability criteria for members subject to buckling and for members subject to special conditions. The equations are based on mechanics principles and are not given in the design code format found in Allowable Stress Design or Load and Resistance Factor Design specifications.

# **Deformation Equations**

Equations for deformation of wood members are presented as functions of applied loads, moduli of elasticity and rigidity, and member dimensions. They may be solved to determine minimum required cross-sectional dimensions to meet deformation limitations imposed in design. Average moduli of elasticity and rigidity are given in Chapter 4. Consideration must be given to variability in material properties and uncertainties in applied loads to control reliability of the design.

# **Axial Load**

The deformation of an axially loaded member is not usually an important design consideration. More important considerations will be presented in later sections dealing with combined loads or stability. Axial load produces a change of length given by

$$\delta = \frac{PL}{AE} \tag{8-1}$$

where  $\delta$  is change of length, L length, A cross-sectional area, E modulus of elasticity ( $E_L$  when grain runs parallel to member axis), and P axial force parallel to grain.

# **Bending**

#### **Straight Beam Deflection**

The deflection of straight beams that are elastically stressed and have a constant cross section throughout their length is given by

$$\delta = \frac{k_b W L^3}{E I} + \frac{k_s W L}{G A'} \tag{8-2}$$

where  $\delta$  is deflection, W total beam load acting perpendicular to beam neutral axis, L beam span,  $k_b$  and  $k_s$  constants dependent upon beam loading, support conditions, and location of point whose deflection is to be calculated, I beam moment of inertia, A' modified beam area, E beam modulus of elasticity (for beams having grain direction parallel to their axis,  $E = E_L$ ), and G beam shear modulus (for beams with flat-grained vertical faces,  $G = G_{LT}$ , and for beams with edgegrained vertical faces,  $G = G_{LR}$ ). Elastic property values are given in Tables 4–1 and 4–2 (Ch. 4).

The first term on the right side of Equation (8–2) gives the bending deflection and the second term the shear deflection. Values of  $k_b$  and  $k_s$  for several cases of loading and support are given in Table 8–1.

The moment of inertia *I* of the beams is given by

$$I = \frac{bh^3}{12}$$
 for beam of rectangular cross section
$$= \frac{\pi d^4}{64}$$
 for beam of circular cross section (8–3)

where b is beam width, h beam depth, and d beam diameter. The modified area A' is given by

$$A' = \frac{5}{6}bh$$
 for beam of rectangular cross section
$$= \frac{9}{40}\pi d^2 \text{ for beam of circular cross section}$$
(8-4)

If the beam has initial deformations such as bow (lateral bend) or twist, these deformations will be increased by the bending loads. It may be necessary to provide lateral or torsional restraints to hold such members in line. (See Interaction of Buckling Modes section.)

### **Tapered Beam Deflection**

Figures 8–1 and 8–2 are useful in the design of tapered beams. The ordinates are based on design criteria such as span, loading, difference in beam height  $(h_c - h_0)$  as required by roof slope or architectural effect, and maximum allowable deflection, together with material properties. From this, the value of the abscissa can be determined and the smallest beam depth  $h_0$  can be calculated for comparison with that given by the design criteria. Conversely, the deflection of a beam can be calculated if the value of the abscissa is known. Tapered beams deflect as a result of shear deflection in addition to bending deflections (Figs. 8–1 and 8–2), and this shear deflection  $\Delta_s$  can be closely approximated by

$$\Delta_{\rm s} = \frac{3WL}{20Gbh_0} \text{ for uniformly distributed load}$$

$$= \frac{3PL}{10Gbh_0} \text{ for midspan-concentrated load}$$
(8–5)

The final beam design should consider the total deflection as the sum of the shear and bending deflection, and it may be necessary to iterate to arrive at final beam dimensions. Equations (8–5) are applicable to either single-tapered or double-tapered beams. As with straight beams, lateral or torsional restraint may be necessary.

#### **Effect of Notches and Holes**

The deflection of beams is increased if reductions in cross-section dimensions occur, such as by holes or notches. The deflection of such beams can be determined by considering them of variable cross section along their length and appropriately solving the general differential equations of the elastic curves,  $EI(d^2y/dx^2) = M$ , to obtain deflection expressions or by the application of Castigliano's theorem. (These procedures are given in most texts on strength of materials.)

Table 8–1. Values of  $k_b$  and  $k_s$  for several beam loadings

Loading	Beam ends	Deflection at	<b>k</b> <sub>b</sub>	<b>k</b> s
Uniformly distributed	Both simply supported	Midspan	5/384	1/8
	Both clamped	Midspan	1/384	1/8
Concentrated at midspan	Both simply supported	Midspan	1/48	1/4
	Both clamped	Midspan	1/192	1/4
Concentrated at outer quarter span points	Both simply supported	Midspan	11/768	1/8
	Both simply supported	Load point	1/96	1/8
Uniformly distributed	Cantilever, one free, one clamped	Free end	1/8	1/2
Concentrated at free end	Cantilever, one free, one clamped	Free end	1/3	1




Figure 8–1. Graph for determining tapered beam size based on deflection under uniformly distributed load.

#### **Effect of Time: Creep Deflections**

In addition to the elastic deflections previously discussed, wood beams usually sag in time; that is, the deflection increases beyond what it was immediately after the load was first applied. (See the discussion of creep in Time Under Load in Ch. 4.)

Green timbers, in particular, will sag if allowed to dry under load, although partially dried material will also sag to some extent. In thoroughly dried beams, small changes in deflection occur with changes in moisture content but with little permanent increase in deflection. If deflection under longtime load with initially green timber is to be limited, it has been customary to design for an initial deflection of about half the value permitted for longtime deflection. If deflection under longtime load with initially dry timber is to be limited, it has been customary to design for an initial deflection of about two-thirds the value permitted for longtime deflection.




Figure 8–2. Graph for determining tapered beam size on deflection under concentrated midspan load.

#### **Water Ponding**

Ponding of water on roofs already deflected by other loads can cause large increases in deflection. The total deflection  $\Delta$  due to design load plus ponded water can be closely estimated by

$$\Delta = \frac{\Delta_0}{1 - S/S_{\rm cr}} \tag{8-6}$$

where  $\Delta_0$  is deflection due to design load alone, S beam spacing, and  $S_{\rm cr}$  critical beam spacing (Eq. (8–31)).

# **Combined Bending and Axial Load**

## **Concentric Load**

Addition of a concentric axial load to a beam under loads acting perpendicular to the beam neutral axis causes increase in bending deflection for added axial compression and decrease in bending deflection for added axial tension.

The deflection under combined loading at midspan for pin-ended members can be estimated closely by

$$\Delta = \frac{\Delta_0}{1 \pm P/P_{\rm cr}} \tag{8--7}$$

where the plus sign is chosen if the axial load is tension and the minus sign if the axial load is compression,  $\Delta$  is midspan deflection under combined loading,  $\Delta_0$  beam midspan deflection without axial load, P axial load, and  $P_{\rm cr}$  a constant equal to the buckling load of the beam under axial compressive load only (see Axial Compression in Stability Equations section.) based on flexural rigidity about the neutral axis perpendicular to the direction of bending loads. This constant appears regardless of whether P is tension or compression. If P is compression, it must be less than  $P_{\rm cr}$  to avoid collapse. When the axial load is tension, it is conservative to ignore the  $P/P_{\rm cr}$  term. (If the beam is not supported against lateral deflection, its buckling load should be checked using Eq. (8–35).)

#### **Eccentric Load**

If an axial load is eccentrically applied to a pin-ended member, it will induce bending deflections and change in length given by Equation (8–1). Equation (8–7) can be applied to find the bending deflection by writing the equation in the form

$$\delta_{\rm b} + \varepsilon_0 = \frac{\varepsilon_0}{1 \pm P/P_{\rm cr}} \tag{8-8}$$

where  $\delta_b$  is the induced bending deflection at midspan and  $\epsilon_0$  the eccentricity of *P* from the centroid of the cross section.

## **Torsion**

The angle of twist of wood members about the longitudinal axis can be computed by

$$\theta = \frac{TL}{GK} \tag{8-9}$$

where  $\theta$  is angle of twist in radians, T applied torque, L member length, G shear modulus (use  $\sqrt{G_{LR}G_{LT}}$ , or approximate G by  $E_L/16$  if measured G is not available), and K a cross-section shape factor. For a circular cross section, K is the polar moment of inertia:

$$K = \frac{\pi D^4}{32} \tag{8-10}$$

where D is diameter. For a rectangular cross section,

$$K = \frac{hb^3}{\Phi} \tag{8-11}$$

where h is larger cross-section dimension, b is smaller cross-section dimension, and  $\phi$  is given in Figure 8–3.




Figure 8–3. Coefficient  $\phi$  for determining torsional rigidity of rectangular member (Eq. (8 –11)).

# **Stress Equations**

The equations presented here are limited by the assumption that stress and strain are directly proportional (Hooke's law) and by the fact that local stresses in the vicinity of points of support or points of load application are correct only to the extent of being statically equivalent to the true stress distribution (St. Venant's principle). Local stress concentrations must be separately accounted for if they are to be limited in design.

## **Axial Load**

#### **Tensile Stress**

Concentric axial load (along the line joining the centroids of the cross sections) produces a uniform stress:

$$f_{\rm t} = \frac{P}{A} \tag{8-12}$$

where  $f_t$  is tensile stress, P axial load, and A cross-sectional area.

# **Short-Block Compressive Stress**

Equation (8–12) can also be used in compression if the member is short enough to fail by simple crushing without deflecting laterally. Such fiber crushing produces a local "wrinkle" caused by microstructural instability. The member as a whole remains structurally stable and able to bear load.

# **Bending**

The strength of beams is determined by flexural stresses caused by bending moment, shear stresses caused by shear load, and compression across the grain at the end bearings and load points.

### Straight Beam Stresses

The stress due to bending moment for a simply supported pin-ended beam is a maximum at the top and bottom edges. The concave edge is compressed, and the convex edge is under tension. The maximum stress is given by

$$f_{\rm b} = \frac{M}{Z} \tag{8-13}$$

where  $f_b$  is bending stress, M bending moment, and Z beam section modulus (for a rectangular cross section,  $Z = bh^2/6$ ; for a circular cross section,  $Z = \pi D^3/32$ ).

This equation is also used beyond the limits of Hooke's law with M as the ultimate moment at failure. The resulting pseudo-stress is called the "modulus of rupture," values of which are tabulated in Chapter 4. The modulus of rupture has been found to decrease with increasing size of member. (See Size Effect section.)

The shear stress due to bending is a maximum at the centroidal axis of the beam, where the bending stress happens to be zero. (This statement is not true if the beam is tapered—see following section.) In wood beams this shear stress may produce a failure crack near mid-depth running along the axis of the member. Unless the beam is sufficiently short and deep, it will fail in bending before shear failure can develop; but wood beams are relatively weak in shear, and shear strength can sometimes govern a design. The maximum shear stress is

$$f_{\rm s} = k \frac{V}{A} \tag{8-14}$$

where  $f_s$  is shear stress, V vertical shear force on cross section, A cross-sectional area, and k = 3/2 for a rectangular cross section or k = 4/3 for a circular cross section.

#### **Tapered Beam Stresses**

For beams of constant width that taper in depth at a slope less than 25°, the bending stress can be obtained from Equation (8–13) with an error of less than 5%. The shear stress, however, differs markedly from that found in uniform beams. It can be determined from the basic theory presented by Maki and Kuenzi (1965). The shear stress at the tapered edge can reach a maximum value as great as that at the neutral axis at a reaction.

Consider the example shown in Figure 8–4, in which concentrated loads farther to the right have produced a support reaction V at the left end. In this case the maximum stresses occur at the cross section that is double the depth of the beam at the reaction. For other loadings, the location of the cross section with maximum shear stress at the tapered edge will be different.

For the beam depicted in Figure 8–4, the bending stress is also a maximum at the same cross section where the shear stress is maximum at the tapered edge. This stress situation also causes a stress in the direction perpendicular to the neutral axis that is maximum at the tapered edge. The effect of combined stresses at a point can be approximately accounted for by an interaction equation based on the Henky–von Mises theory of energy due to the change of shape. This theory applied by Norris (1950) to wood results in

$$\frac{f_x^2}{F_x^2} + \frac{f_{xy}^2}{F_{xy}^2} + \frac{f_y^2}{F_y^2} = 1$$
 (8–15)

where  $f_x$  is bending stress,  $f_y$  stress perpendicular to the neutral axis, and  $f_{xy}$  shear stress. Values of  $F_x$ ,  $F_y$ , and  $F_{xy}$  are corresponding stresses chosen at design values or maximum values in accordance with allowable or maximum values being determined for the tapered beam. Maximum stresses in




Figure 8-4. Shear stress distribution for a tapered beam.

the beam depicted in Figure 8-4 are given by

$$f_x = \frac{3M}{2bh_0^2}$$

$$f_{xy} = f_x \tan \theta$$

$$f_y = f_x \tan^2 \theta$$
(8-16)

Substitution of these equations into the interaction Equation (8–15) will result in an expression for the moment capacity M of the beam. If the taper is on the beam tension edge, the values of  $f_x$  and  $f_y$  are tensile stresses.

**Example**: Determine the moment capacity (newton-meters) of a tapered beam of width b = 100 mm, depth  $h_0 = 200$  mm, and taper tan  $\theta = 1/10$ . Substituting these dimensions into Equation (8–16) (with stresses in pascals) results in

$$f_x = 375M$$
$$f_{xy} = 37.5M$$
$$f_y = 3.75M$$

Substituting these into Equation (8–15) and solving for M results in

$$M = \frac{1}{3.75 \left[ 10^4 / F_x^2 + 10^2 / F_{xy}^2 + 1 / F_y^2 \right]^{1/2}}$$

where appropriate allowable or maximum values of the F stresses (pascals) are chosen.

## Size Effect

The modulus of rupture (maximum bending stress) of wood beams depends on beam size and method of loading, and the strength of clear, straight-grained beams decreases as size increases. These effects were found to be describable by statistical strength theory involving "weakest link" hypotheses and can be summarized as follows: For two beams under two equal concentrated loads applied symmetrical to the midspan points, the ratio of the modulus of rupture of beam 1 to the modulus of rupture of beam 2 is given by

$$\frac{R_1}{R_2} = \left[ \frac{h_2 L_2 (1 + ma_2 / L_2)}{h_1 L_1 (1 + ma_1 / L_1)} \right]^{1/m}$$
(8-17)

where subscripts 1 and 2 refer to beam 1 and beam 2, R is modulus of rupture, h beam depth, L beam span, a distance between loads placed a/2 each side of midspan, and m a constant. For clear, straight-grained Douglas-fir beams, m = 18. If Equation (8–17) is used for beam 2 size (Ch. 4) loaded at midspan, then  $h_2 = 5.08$  mm (2 in.),  $L_2 = 71.112$  mm (28 in.), and  $a_2 = 0$  and Equation (8–17) becomes

$$\frac{R_1}{R_2} = \left[ \frac{361.29}{h_1 L_1 (1 + ma_1/L_1)} \right]^{1/m}$$
 (metric) (8–18a)

$$\frac{R_1}{R_2} = \left[ \frac{56}{h_1 L_1 (1 + ma_1 / L_1)} \right]^{1/m}$$
 (inch-pound) (8–18b)

**Example:** Determine modulus of rupture for a beam 10 in. deep, spanning 18 ft, and loaded at one-third span points compared with a beam 2 in. deep, spanning 28 in., and loaded at midspan that had a modulus of rupture of  $10,000 \text{ lb/in}^2$ . Assume m = 18. Substituting the dimensions into Equation (8–18) produces

$$R_1 = 10,000 \left[ \frac{56}{2,160(1+6)} \right]^{1/18}$$
$$= 7,330 \text{ lb/in}^2$$

Application of the statistical strength theory to beams under uniformly distributed load resulted in the following relationship between modulus of rupture of beams under uniformly distributed load and modulus of rupture of beams under concentrated loads:

$$\frac{R_{\rm u}}{R_{\rm c}} = \left[ \frac{\left(1 + 18a_{\rm c}/L_{\rm c}\right)h_{\rm c}L_{\rm c}}{3.876h_{\rm u}L_{\rm u}} \right]^{1/18}$$
(8–19)

where subscripts u and c refer to beams under uniformly distributed and concentrated loads, respectively, and other terms are as previously defined.

Shear strength for non-split, non-checked, solid-sawn, and glulam beams also decreases as beam size increases. A relationship between beam shear  $\tau$  and ASTM shear block strength  $\tau_{\text{ASTM}}$ , including a stress concentration factor for the re-entrant corner of the shear block,  $C_{\text{f}}$ , and the shear area A, is

$$\tau = \frac{1.9C_f \tau_{ASTM}}{A^{1/5}}$$
 (metric) (8–20a)

$$\tau = \frac{1.3C_f \tau_{ASTM}}{A^{1/5}}$$
 (inch-pound) (8–20b)

where  $\tau$  is beam shear (MPa, lb/in<sup>2</sup>),  $C_f$  stress concentration factor,  $\tau_{ASTM}$  ASTM shear block strength (MPa, lb/in<sup>2</sup>), and A shear area (cm<sup>2</sup>, in<sup>2</sup>).

This relationship was determined by empirical fit to test data. The shear block re-entrant corner concentration factor is approximately 2; the shear area is defined as beam width multiplied by the length of beam subjected to shear force.

# Effect of Notches, Slits, and Holes

In beams having notches, slits, or holes with sharp interior corners, large stress concentrations exist at the corners. The local stresses include shear parallel to grain and tension




Figure 8–5. Coefficients A and B for crack-initiation criterion (Eq. (8–21)).

perpendicular to grain. As a result, even moderately low loads can cause a crack to initiate at the sharp corner and propagate along the grain. An estimate of the crack-initiation load can be obtained by the fracture mechanics analysis of Murphy (1979) for a beam with a slit, but it is generally more economical to avoid sharp notches entirely in wood beams, especially large wood beams, since there is a size effect: sharp notches cause greater reductions in strength for larger beams. A conservative criterion for crack initiation for a beam with a slit is

$$\sqrt{h} \left[ A \left( \frac{6M}{bh^2} \right) + B \left( \frac{3V}{2bh} \right) \right] = 1 \tag{8-21}$$

where h is beam depth, b beam width, M bending moment, and V vertical shear force, and coefficients A and B are presented in Figure 8–5 as functions of a/h, where a is slit depth. The value of A depends on whether the slit is on the tension edge or the compression edge. Therefore, use either  $A_t$  or  $A_c$  as appropriate. The values of A and B are dependent upon species; however, the values given in Figure 8–5 are conservative for most softwood species.

# Effects of Time: Creep Rupture, Fatigue, and Aging

See Chapter 4 for a discussion of fatigue and aging. Creep rupture is accounted for by duration-of-load adjustment in the setting of allowable stresses, as discussed in Chapters 4 and 6.

## **Water Ponding**

Ponding of water on roofs can cause increases in bending stresses that can be computed by the same amplification factor (Eq. (8–6)) used with deflection. (See Water Ponding in the Deformation Equations section.)

# **Combined Bending and Axial Load**

#### Concentric Load

Equation (8–7) gives the effect on deflection of adding an end load to a simply supported pin-ended beam already bent by transverse loads. The bending stress in the member is modified by the same factor as the deflection:

$$f_{\rm b} = \frac{f_{\rm b0}}{1 \pm P/P_{\rm cr}} \tag{8-22}$$

where the plus sign is chosen if the axial load is tension and the minus sign is chosen if the axial load is compression,  $f_b$  is net bending stress from combined bending and axial load,  $f_{b0}$  bending stress without axial load, P axial load, and  $P_{cr}$  the buckling load of the beam under axial compressive load only (see Axial Compression in the Stability Equations section), based on flexural rigidity about the neutral axis perpendicular to the direction of the bending loads. This  $P_{cr}$  is not necessarily the minimum buckling load of the member. If P is compressive, the possibility of buckling under combined loading must be checked. (See Interaction of Buckling Modes.)

The total stress under combined bending and axial load is obtained by superposition of the stresses given by Equations (8–12) and (8–22).

**Example:** Suppose transverse loads produce a bending stress  $f_{b0}$  tensile on the convex edge and compressive on the concave edge of the beam. Then the addition of a tensile axial force P at the centroids of the end sections will produce a maximum tensile stress on the convex edge of

$$f_{\text{t max}} = \frac{f_{\text{b0}}}{1 + P/P_{\text{cr}}} + \frac{P}{A}$$

and a maximum compressive stress on the concave edge of

$$f_{\rm c max} = \frac{f_{\rm b0}}{1 + P/P_{\rm cr}} - \frac{P}{A}$$

where a negative result would indicate that the stress was in fact tensile.

### **Eccentric Load**

If the axial load is eccentrically applied, then the bending stress  $f_{b0}$  should be augmented by  $\pm P\epsilon_0/Z$ , where  $\epsilon_0$  is eccentricity of the axial load.

**Example:** In the preceding example, let the axial load be eccentric toward the concave edge of the beam. Then the maximum stresses become

$$f_{\text{t max}} = \frac{f_{\text{b0}} - P\varepsilon_0/Z}{1 + P/P_{\text{cr}}} + \frac{P}{A}$$

$$f_{\rm c max} = \frac{f_{\rm b0} - P\varepsilon_0/Z}{1 + P/P_{\rm cr}} - \frac{P}{A}$$

# **Torsion**

For a circular cross section, the shear stress induced by torsion is

$$f_{\rm s} = \frac{16T}{\pi D^3} \tag{8-23}$$

where T is applied torque and D diameter. For a rectangular cross section,

$$f_{\rm s} = \frac{T}{\beta h b^2} \tag{8-24}$$

where T is applied torque, h larger cross-section dimension, and b smaller cross-section dimension, and  $\beta$  is presented in Figure 8–6.

# **Stability Equations**

# **Axial Compression**

For slender members under axial compression, stability is the principal design criterion. The following equations are for concentrically loaded members. For eccentrically loaded columns, see Interaction of Buckling Modes section.

# **Long Columns**

A column long enough to buckle before the compressive stress P/A exceeds the proportional limit stress is called a "long column." The critical stress at buckling is calculated by Euler's formula:

$$f_{\rm cr} = \frac{\pi^2 E_L}{(L/r)^2}$$
 (8–25)

where  $E_L$  is elastic modulus parallel to the axis of the member, L unbraced length, and r least radius of gyration (for a rectangular cross section with b as its least dimension,

 $r = b/\sqrt{12}$ , and for a circular cross section, r = d/4). Equation (8–25) is based on a pinned-end condition but may be used conservatively for square ends as well.

## **Short Columns**

Columns that buckle at a compressive stress *P/A* beyond the proportional limit stress are called "short columns." Usually the short column range is explored empirically, and appropriate design equations are proposed. Material of this nature is presented in *USDA Technical Bulletin 167* (Newlin and Gahagan 1930). The final equation is a fourth-power parabolic function that can be written as

$$f_{\rm cr} = F_{\rm c} \left[ 1 - \frac{4}{27\pi^4} \left( \frac{L}{r} \sqrt{\frac{F_{\rm c}}{E_L}} \right)^4 \right]$$
 (8–26)




Figure 8–6. Coefficient  $\beta$  for computing maximum shear stress in torsion of rectangular member (Eq. (8 –24)).




Figure 8–7. Graph for determining critical buckling stress of wood columns.

where  $F_c$  is compressive strength and remaining terms are defined as in Equation (8–25). Figure 8–7 is a graphical representation of Equations (8–25) and (8–26).

Short columns can be analyzed by fitting a nonlinear function to compressive stress–strain data and using it in place of Hooke's law. One such nonlinear function proposed by Ylinen (1956) is

$$\varepsilon = \frac{F_{\rm c}}{E_L} \left[ c \frac{f}{F_{\rm c}} - (1 - c) \log_e \left( 1 - \frac{f}{F_{\rm c}} \right) \right]$$
 (8–27)

where  $\varepsilon$  is compressive strain, f compressive stress, c a constant between 0 and 1, and  $E_L$  and  $F_c$  are as previously defined. Using the slope of Equation (8–27) in place of  $E_L$  in Euler's formula (Eq. (8–25)) leads to Ylinen's buckling equation

$$f_{\rm cr} = \frac{F_{\rm c} + f_{\rm e}}{2c} - \sqrt{\left(\frac{F_{\rm c} + f_{\rm e}}{2c}\right)^2 - \frac{F_{\rm c} f_{\rm e}}{c}}$$
 (8–28)

where  $F_c$  is compressive strength and  $f_c$  buckling stress given by Euler's formula (Eq. (8–25)). Equation (8–28) can be made to agree closely with Figure 8–7 by choosing c = 0.957.

Comparing the fourth-power parabolic function Equation (8–26) to experimental data indicates the function is nonconservative for intermediate L/r range columns. Using Ylinen's buckling equation with c=0.8 results in a better approximation of the solid-sawn and glued-laminated data.

# **Built-Up and Spaced Columns**

Built-up columns of nearly square cross section with the lumber nailed or bolted together will not support loads as great as if the lumber were glued together. The reason is that shear distortions can occur in the mechanical joints.

If built-up columns are adequately connected and the axial load is near the geometric center of the cross section, Equation (8–28) is reduced with a factor that depends on the type of mechanical connection. The built-up column capacity is

$$f_{\rm cr} = K_{\rm f} \left[ \frac{F_{\rm c} + f_{\rm e}}{2c} - \sqrt{\left(\frac{F_{\rm c} + f_{\rm e}}{2c}\right)^2 - \frac{F_{\rm c} f_{\rm e}}{c}} \right]$$
 (8–29)

where  $F_c$ ,  $f_e$ , and c are as defined for Equation (8–28).  $K_f$  is the built-up stability factor, which accounts for the efficiency of the connection; for bolts,  $K_f = 0.75$ , and for nails,  $K_f = 0.6$ , provided bolt and nail spacing requirements meet design specification approval.

If the built-up column is of several spaced pieces, the spacer blocks should be placed close enough together, lengthwise in the column, so that the unsupported portion of the spaced member will not buckle at the same or lower stress than that of the complete member. "Spaced columns" are designed with previously presented column equations, considering each compression member as an unsupported simple column; the sum of column loads for all the members is taken as the column load for the spaced column.

#### **Columns With Flanges**

Columns with thin, outstanding flanges can fail by elastic instability of the outstanding flange, causing wrinkling of the flange and twisting of the column at stresses less than those for general column instability as given by Equations (8–25) and (8–26). For outstanding flanges of cross sections such as I, H,  $^+$ , and L, the flange instability stress can be estimated by

$$f_{\rm cr} = 0.044E \frac{t^2}{b^2} \tag{8-30}$$

where E is column modulus of elasticity, t thickness of the outstanding flange, and b width of the outstanding flange. If the joints between the column members are glued and reinforced with glued fillets, the instability stress increases to as much as 1.6 times that given by Equation (8–30).

# **Bending**

Beams are subject to two kinds of instability: lateral—torsional buckling and progressive deflection under water ponding, both of which are determined by member stiffness.

#### **Water Ponding**

Roof beams that are insufficiently stiff or spaced too far apart for their given stiffness can fail by progressive deflection under the weight of water from steady rain or another continuous source. The critical beam spacing  $S_{cr}$  is given by

$$S_{\rm cr} = \frac{m\pi^4 EI}{\rho L^4} \tag{8-31}$$

where E is beam modulus of elasticity, I beam moment of inertia,  $\rho$  density of water (1,000 kg/m<sup>3</sup>, 0.0361 lb/in<sup>3</sup>), L beam length, and m = 1 for simple support or m = 16/3 for fixed-end condition. To prevent ponding, the beam spacing must be less than  $S_{cr}$ .

## Lateral-Torsional Buckling

Since beams are compressed on the concave edge when bent under load, they can buckle by a combination of lateral deflection and twist. Because most wood beams are rectangular in cross section, the equations presented here are for rectangular members only. Beams of I, H, or other built-up cross section exhibit a more complex resistance to twisting and are more stable than the following equations would predict.

**Long Beams**—Long slender beams that are restrained against axial rotation at their points of support but are otherwise free to twist and to deflect laterally will buckle when the maximum bending stress  $f_b$  equals or exceeds the following critical value:

$$f_{\rm b\,cr} = \frac{\pi^2 E_L}{\alpha^2} \tag{8-32}$$

where  $\alpha$  is the slenderness factor given by

$$\alpha = \sqrt{2\pi} \sqrt[4]{\frac{EI_y}{GK}} \frac{\sqrt{L_e h}}{h}$$
 (8-33)

where  $EI_y$  is lateral flexural rigidity equal to  $E_L hb^3/12$ , h is beam depth, b beam width, GK torsional rigidity defined in Equation (8–9), and  $L_e$  effective length determined by type of loading and support as given in Table 8–2. Equation (8–32) is valid for bending stresses below the proportional limit.

**Short Beams**—Short beams can buckle at stresses beyond the proportional limit. In view of the similarity of Equation (8–32) to Euler's formula (Eq. (8–25)) for column buckling, it is recommended that short-beam buckling be analyzed by using the column buckling criterion in Figure 8–7 applied with  $\alpha$  in place of L/r on the abscissa

Table 8–2. Effective length for checking lateral–torsional stability of beams<sup>a</sup>

Support	Load	Effective length $L_{\rm e}$
Simple support	Equal end moments	L
	Concentrated force at center	$\frac{0.742L}{1-2h/L}$
	Uniformly distributed force	$\frac{0.887L}{1-2h/L}$
Cantilever	Concentrated force at end	$\frac{0.783L}{1-2h/L}$
	Uniformly distributed force	$\frac{0.489L}{1 - 2  h/L}$

<sup>&</sup>lt;sup>a</sup>These values are conservative for beams with a width-to-depth ratio of less than 0.4. The load is assumed to act at the top edge of the beam.

and  $f_{\rm b\,cr}/F_{\rm b}$  in place of  $f_{\rm cr}/F_{\rm c}$  on the ordinate. Here  $F_{\rm b}$  is beam modulus of rupture.

Effect of Deck Support—The most common form of support against lateral deflection is a deck continuously attached to the top edge of the beam. If this deck is rigid against shear in the plane of the deck and is attached to the compression edge of the beam, the beam cannot buckle. In regions where the deck is attached to the tension edge of the beam, as where a beam is continuous over a support, the deck cannot be counted on to prevent buckling and restraint against axial rotation should be provided at the support point.

If the deck is not very rigid against in-plane shear, as for example standard 38-mm (nominal 2-in.) wood decking, Equation (8–32) and Figure 8–7 can still be used to check stability except that now the effective length is modified by dividing by  $\theta$ , as given in Figure 8–8. The abscissa of this figure is a deck shear stiffness parameter  $\tau$  given by

$$\tau = \frac{SG_{\rm D}L^2}{EI_{\rm w}} \tag{8-34}$$

where  $EI_y$  is lateral flexural rigidity as in Equation (8–33), S beam spacing,  $G_D$  in-plane shear rigidity of deck (ratio of shear force per unit length of edge to shear strain), and L actual beam length. This figure applies only to simply supported beams. Cantilevers with the deck on top have their tension edge supported and do not derive much support from the deck.




Figure 8–8. Increase in buckling stress resulting from attached deck; simply supported beams. To apply this graph, divide the effective length by  $\theta$ .

# Interaction of Buckling Modes

When two or more loads are acting and each of them has a critical value associated with a mode of buckling, the combination can produce buckling even though each load is less than its own critical value.

The general case of a beam of unbraced length  $l_e$  includes a primary (edgewise) moment  $M_1$ , a lateral (flatwise) moment  $M_2$ , and axial load P. The axial load creates a secondary moment on both edgewise and flatwise moments due to the deflection under combined loading given by Equation (8–7). In addition, the edgewise moment has an effect like the secondary moment effect on the flatwise moment.

The following equation contains two moment modification factors, one on the edgewise bending stress and one on the flatwise bending stress that includes the interaction of biaxial bending. The equation also contains a squared term for axial load to better predict experimental data:

$$\begin{split} \left(\frac{f_{\rm c}}{F_{\rm c}}\right)^2 + \frac{f_{\rm bl} + 6(e_1/d_1)f_{\rm c}(1.234 - 0.234\theta_{\rm cl})}{\theta_{\rm cl}F_{\rm bl}'} \\ + \frac{f_{\rm b2} + 6(e_2/d_2)f_{\rm c}(1.234 - 0.234\theta_{\rm c2})}{\theta_{\rm c2}F_{\rm b2}'} \leq 1.0 \end{split} \tag{8-35}$$

where f is actual stress in compression, edgewise bending, or flatwise bending (subscripts c, b1, or b2, respectively), F buckling strength in compression or bending (a single prime denotes the strength is reduced for slenderness), e/d ratio of eccentricity of the axial compression to member depth ratio for edgewise or flatwise bending (subscripts 1 or 2, respectively), and  $\theta_c$  moment magnification factors for edgewise and flatwise bending, given by

$$\theta_{\rm cl} = 1 - \left(\frac{f_{\rm c}}{F_{\rm cl}''} + \frac{S}{S_{\rm cr}}\right)$$
 (8–36)

$$\theta_{c2} = 1 - \left(\frac{f_c}{F_{c2}^{"}} + \frac{f_{b1} + 6(e_1/d_1)f_c}{F_{b1}^{"}}\right)$$
(8–37)

$$F_{\rm cl}^{"} = \frac{0.822E}{\left(l_{\rm el}/d_{\rm i}\right)^2} \tag{8-38}$$

$$F_{\rm c2}'' = \frac{0.822E}{(l_{\rm e2}/d_2)^2} \tag{8-39}$$

$$F_{\rm bl}'' = \frac{1.44E}{l_{\rm e}} \frac{d_2}{d_1} \tag{8-40}$$

where  $l_e$  is effective length of member and S and  $S_{cr}$  are previously defined ponding beam spacing.

# References

**ASTM.** [current edition]. Standard methods for testing clear specimens of timber. ASTM D143–94. West Conshohocken, PA: American Society for Testing and Materials.

**Bohannan, B.** 1966. Effect of size on bending strength of wood members. Res. Pap. FPL–RP–56. Madison, WI: U.S. Department of Agriculture, Forest Service, Forest Products Laboratory.

**Gerhardt, T.D.; Liu, J.Y.** 1983. Orthotropic beams under normal and shear loading. Journal of Engineering Mechanics, ASCE. 109(2): 394–410.

**Kuenzi, E.W.; Bohannan, B.** 1964. Increases in deflection and stress caused by ponding of water on roofs. Forest Products Journal. 14(9): 421–424.

**Liu, J.Y.** 1980. Shear strength of wood beams: A Weibull analysis. Journal of Structural Division, ASCE. 106(ST10): 2035–2052.

**Liu, J.Y.** 1981. Shear strength of tapered wood beams. Journal of Structural Division, ASCE. 107(ST5): 719–731.

**Liu, J.Y.** 1982. A Weibull analysis of wood member bending strength. Transactions, American Society of Mechanical Engineers. Journal of Mechanical Design. 104: 572–579.

**Liu, J.Y.** 1984. Evaluation of the tensor polynomial strength theory for wood. Journal of Composite Materials. 18(3): 216–226. (May).

**Liu, J.Y.; Cheng, S.** 1979. Analysis of orthotropic beams. Res. Pap. FPL–RP–343. Madison, WI: U.S. Department of Agriculture, Forest Service, Forest Products Laboratory.

**Maki, A C.; Kuenzi, E.W.** 1965. Deflection and stresses of tapered wood beams. Res. Pap. FPL–RP–34. Madison, WI: U.S. Department of Agriculture, Forest Service, Forest Products Laboratory.

Malhorta, S.K.; Sukumar, A.P. 1989. A simplied procedure for built-up wood compression members. St. Johns,

New Foundland: Annual conference, Canadian Society for Civil Engineering: 1–18 (June).

**Murphy, J.F.** 1979. Using fracture mechanics to predict failure of notched wood beams. In: Proceedings of first international conference on wood fracture; 1978, Aug. 14–16; Banff, AB. Vancouver, BC: Forintek Canada Corporation: 159: 161–173.

**Newlin, J.A.; Gahagan, J.M.** 1930. Tests of large timber columns and presentation of the Forest Products Laboratory column formula. Tech. Bull. 167. Madison, WI: U.S. Department of Agriculture, Forest Service, Forest Products Laboratory.

**Newlin, J.A.; Trayer, G.W.** 1924. Deflection of beams with special reference to shear deformations. Rep. 180. Washington, DC: U.S. National Advisory Committee on Aeronautics.

**Norris, C.B.** 1950. Strength of orthotropic materials subjected to combined stresses. Rep. 1816. Madison, WI: U.S. Department of Agriculture, Forest Service, Forest Products Laboratory.

Rammer, D.R.; Soltis, L.A. 1994. Experimental shear strength of glued-laminated beams. Res. Rep. FPL–RP–527. Madison, WI, U.S. Department of Agriculture, Forest Service, Forest Products Laboratory.

Rammer, D.R.; Soltis, L.A.; Lebow, P.K. 1996. Experimental shear strength of unchecked solid sawn Douglas-fir. Res. Pap. FPL–RP–553. Madison, WI: U.S. Department of Agriculture, Forest Service, Forest Products Laboratory.

**Soltis, L.A., Rammer, D.R.** 1997. Bending to shear ratio approach to beam design. Forest Products Journal. 47(1): 104–108.

**Trayer, G.W.** 1930. The torsion of members having sections common in aircraft construction. Rep. 334. Washington, DC: U.S. National Advisory Committee on Aeronautics.

**Trayer, G.W.; March, H.W.** 1931. Elastic instability of members having sections common in aircraft construction. Rep. 382. Washington, DC: U.S. National Advisory Committee on Aeronautics.

**Ylinen, A.** 1956. A method of determining the buckling stress and the required cross-sectional area for centrally loaded straight columns in elastic and inelastic range. Publication of the International Association for Bridge and Structural Engineering. Zurich. Vol. 16.

**Zahn, J.J.** 1973. Lateral stability of wood beam-and-deck systems. Journal of the Structural Division, ASCE. 99(ST7): 1391–1408.

**Zahn, J.J.** 1986. Design of wood members under combined loads. Journal of Structural Engineering, ASCE. 112(ST9): 2109–2126.

**Zahn, J.J.** 1988. Combined-load stability criterion for wood beam-columns. Journal of Structural Engineering, ASCE. 114(ST11): 2612–2628.

# From

Forest Products Laboratory. 1999. Wood handbook—Wood as an engineering material. Gen. Tech. Rep. FPL–GTR–113. Madison, WI: U.S. Department of Agriculture, Forest Service, Forest Products Laboratory. 463 p.