

Seneca Hardood RQ(?) vs FS

# 4 different pieces – cross section

**100% Flat Sawn** – The growth rings are CLEARLY horizontal



**100% Flat Sawn**

**50% Flat Sawn**

Right edge growth rings  
are  $> 60^\circ$

**100% Quarter sawn**

The growth rings are  
fully vertical

The top 3 pieces are from Seneca and the  
last one is from another mill

# Face view

Clearly shows the typical FS grain pattern

Clear RQ pattern



50% straight grain and 50% typical FS grain